

International Journal of Engineering Research and Science & Technology



www.ijerst.org

ISSN : 2319-5991

Vol. 22 No. 2(1) (2026)



ijerst.editor@gmail.com
editor@ijerst.com

Research Paper

Experimental Investigation on Strength and Durability of Concrete with Different Bacteria

D. Vannurvali¹, B. Prakash²

¹M. Tech Student, Department of Civil Engineering, P.V.K.K Institute of Technology, Alamuru Road, Anantapur, Andhra Pradesh 515002

²Assistant Professor, Department of Civil Engineering, P.V.K.K Institute of Technology, Alamuru Road, Anantapur, Andhra Pradesh 515002

ABSTRACT- Concrete is a very essential factor among creation materials that is widely been in use in infrastructure. Despite of its vital usage for production functions, it nevertheless has numerous obstacles. It is expected that production of cement alone contributes to approximately 7% of world anthropogenic CO₂ emissions that is accountable for green residence effect resulting in worldwide warming. The most important disadvantage of concrete is its low tensile electricity due to which micro crack occurs whilst the burden carried out is more than its limit and this paves way for the seepage of water and other salts. This initiates corrosion and makes the whole structure vulnerable and leads to the failure of shape. To remediate this sort of failure due to cracks and fissures, an approach of the usage of bio mineralization in concrete has advanced in latest years.

The concrete structures have various sturdiness problems due to the special physiological conditions and it outcomes to irretrievable harm to the structure and ultimately discount within the strength of concrete structure. The essential cause behind the downgrading of the durability and mechanical aspects of concrete is the pore structure of concrete. In the current years MICCP (microbiologically triggered calcium carbonate precipitation) by the bacteria taken into consideration as an surroundings pleasant method to decorate the properties of concrete, also for the repair of concrete structure and to consolidate unique construction materials.

This paper gives a observe is carried out to test the Compressive strength, Split tensile electricity, Flexural strength and sturdiness of bacterial concrete through using three one of a kind varieties of bacteria with various dosages like 0ml, 5ml, 10ml, 15ml, 20ml for the M30 and M40 Grade concrete.

I. INTRODUCTION

Concrete is an adaptable fabric having lower ductile and shear first-class. Essentially, concrete is fragile material and carries a terrific many smaller scale breaks show inside the body. The flexibility of cement

is fairly steady at low emotions of hysteria however starts diminishing at better emotions of hysteria as network begins splitting. Concrete has a low coefficient of heat extension, and as it develops stable psychologists. Every stable shape will spoil to a few

diploma, due to shrinkage and stress. Solid which is subjected to lengthy-span powers is willing to move slowly. Presently not unusual and pretend strands are utilized to beautify execution and amplify the inability of cement for elite. The regular problem located in structures is Crack.

Objectives of the study:

The main objective is divided into following for the current study

1. To study the variation of compressive strength of concrete with bacteria for M30 and M40 Grade concrete.
2. To study the split tensile strength, flexural strength of concrete
3. To study the durability of concrete by using Bacteria
4. To create self-healing property.
5. To reduce the maintenance repair cost.

II. LITERATURE REVIEW

Dr. S. Siddiraju¹, N. Ganesh Babu², et al.(2015)

From the research it became presumed that Compressive first-rate of 5% Bacterial mixture considerably increments to 2.63% while contrasted and Control mixture. Compressive best of 10% Calcium lactate increments to 2.63% whilst contrasted and Control combo. Past 10% of Calcium lactate there's 20.80% diminishing in compressive fine of cement.

Meera C M and Dr Subha V2

They have disbursed a paper on Strength And Durability appraisal Of Bacteria Based Self-Healing Concrete. In this paper they have got tested approximately the effect of Bacillus subtilis JC3 at the exceptional and energy of cement. They utilized three-D shapes of sizes 150mm x 150mm x 150mm and

chambers with a distance across of 100mm and a stature of 200mm with and with out expansion of small scale residing beings, of M20 assessment concrete.

III. MATERIALS AND MIX DESIGN

Cement: Cement is a fastener, a substance used underway that gadgets and solidifies and may tie different materials collectively. For this study cement of OPC 53 Grade used.

Aggregates- Development of aggregates, or absolutely "mixture", is a fantastic class of coarse particulate texture utilized underway, along with sand, rock, overwhelmed stone, slag, reused concrete and geo-fake totals. Totals are the maximum mined materials within the global

Coarse aggregate-

For this study size of coarse aggregates of 20mm was used with

Specific gravity = 2.98

Fineness modulus = 7.5


Fine aggregate- Locally handy shimmering sand, detached from ordinary test quantity is utilized. The outcome of sifter evaluation affirms it to Zone-II (in advance with IS: 383-1970).The checks are performed and outcomes are tested as follows.

- Specific gravity = 2.3
- Fineness modulus = 3.06

Water- Generally potable water ought to be used.

Bacteria

Bacillus Pasteurii- Bacillus pasteurii previously referred to as Sporosarcina pasteurii. Pasteurii has been proposed to be utilized as a obviously strong organic improvement material.



Bacillus pasteurii


Bacillus Subtilis- Initially named vibrio subtilis in 1835, Bacillus subtilis microscopic organisms were one of the main microbes to be examined. These microbes are a decent model for cell advancement and differential (Entrez Genome Project).



Bacillus subtilis

Bacillus Sphaericus-

Lysinibacillus sphaericus (renamed - beforehand known as Bacillus sphaericus). It can frame safe endospores that are tolerant to high temperatures, synthetic concoctions and bright light and can stay practical for extensive stretches of time.



Bacillus sphaericus

MIX DESIGN OF CONCRETE

For M30 Grade Concrete is 0.50 : 1 : 1.86 : 2.89

For M30 Grade Concrete is 0.40 : 1 : 1.35 : 2.65

IV EXPERIMENTAL INVESTIGATION

Mixing of Concrete:

The concrete is to be mixed by hand or by the utilization of research center cluster blender so as to keep away from misfortune in water and different materials



Concrete Mixer



Mixing the concrete

WORKABILITY TESTS

Workability of concrete depicts the simplicity or trouble with which the concrete is taken care of, transported and placed between the structures with least loss of homogeneity.

PREPARATION OF CONCRETE CUBES

MOULDS

Moulds to be used for casting of cubes are commonly fabricated from metals like solid iron or metal, sturdy sufficient to save you the distortions. The moulds must facilitate smooth elimination of

cubes when preliminary energy is attained. The dimensions and the internal faces are required to be accurate inside the following limits.

The height of the mildew and the gap among the opposites faces are of precise length $\pm 0.2\text{mm}$, the angle between the adjoining internal faces and pinnacle and backside plates of the mould to be 90 ± 0.50 . The interior faces of the mold are aircraft surfaces with permissible versions $\pm 0.03\text{mm}$. Each mildew is furnished with a steel base plate having aircraft surface.



Preparation of Concrete cube

Compaction

As soon as the integration is completed, test specimens are to be organized in this sort of manner to produce complete compaction. The concrete is stuffed into the mould inside the layers about 5cm deep.

CURING

That test specimen will be stored on the web site from wherein vibrations, under damp matting, sacks or the similar materials for 24 hours from the time of addition of water to the alternative ingredients. The temperature of the vicinity of garage shall be in the

range of 22°C to 32°C . After the duration of 24 hours, they will be marked for later identification, eliminated from the moulds and, except required for checking out, re saved in clean water at a temperature of 24°C to 30°C until they may be transported to laboratory for destiny tests.

TESTING OF CONCRETE

Tests to be conducted on fresh concrete

1. Slump cone test
2. Compaction factor test

Tests to be conducted on Hardened concrete

1. Compressive strength
2. Split tensile strength
3. Flexural strength
4. Durability
5. Healing of concrete

V RESULTS AND ANALYSIS

Slump cone test

% Bacteria used	M30 Grade Concrete			M40 Grade Concrete		
	Bacillus Pasterni	Bacillus Subtilis	Bacillus sphaericus	Bacillus Pasterni	Bacillus Subtilis	Bacillus sphaericus
0ml	25	25	25	28	30	30
5ml	27	28	30	35	35	33
10ml	30	35	33	40	40	38
15ml	35	38	40	45	43	40
20ml	40	42	45	50	45	45

Compaction factor test

% Bacteria used	M30 Grade Concrete			M40 Grade Concrete		
	Bacillus Pasterni	Bacillus Subtilis	Bacillus sphaericus	Bacillus Pasterni	Bacillus Subtilis	Bacillus sphaericus
0ml	0.94	0.92	0.9	0.92	0.9	0.9
5ml	0.92	0.88	0.86	0.84	0.86	0.88
10ml	0.9	0.84	0.82	0.8	0.84	0.84
15ml	0.84	0.8	0.78	0.76	0.8	0.8
20ml	0.82	0.76	0.74	0.74	0.76	0.74

Compressive strength of concrete

For M30 Grade Concrete

S.no	Bacteria used	M30 Grade Concrete								
		Compressive strength of concrete by using Bacillus pasteurii			Compressive strength of concrete by using Bacillus subtilis			Compressive strength of concrete by using Bacillus sphaericus		
		7days	14days	28days	7days	14days	28days	7days	14days	28days
1	0ml	19.8	26.6	29.4	19.8	26.6	29.4	19.8	26.6	29.4
2	5ml	20.4	27.2	30.24	20.8	27.1	29.84	20.44	27.26	29.92
3	10ml	20.64	27.46	30.48	20.98	27.36	30.06	20.66	27.52	30.54
4	15ml	20.46	27.3	30.26	20.86	27.3	29.98	20.6	27.44	30.4
5	20ml	20.34	27.16	30.12	20.68	27.14	29.64	20.42	27.22	30.28

For M40 Grade Concrete

S.no	Bacteria used	M40 Grade Concrete								
		Compressive strength of concrete by using Bacillus pasteurii			Compressive strength of concrete by using Bacillus subtilis			Compressive strength of concrete by using Bacillus sphaericus		
		7days	14days	28days	7days	14days	28days	7days	14days	28days
1	0ml	25.6	35.8	39.38	25.6	35.8	39.38	25.6	35.8	39.38
2	5ml	26.1	36.14	39.56	26.22	36.24	39.68	26.32	36.46	39.78
3	10ml	26.68	36.44	40.2	26.92	36.52	40.52	27.04	36.64	40.72
4	15ml	26.02	36.26	40.06	26.84	36.26	40.44	27.18	36.74	40.4
5	20ml	25.86	35.88	39.92	26.66	36.04	40.12	26.86	36.52	40.18

Split tensile strength of concrete

For M30 Grade Concrete

S.no	Bacteria used	Split tensile strength of concrete by using Bacillus pasteurii		Split tensile strength of concrete by using Bacillus subtilis		Split strength of concrete by using Bacillus sphaericus	
		14days	28days	14days	28days	14days	28days
		14days	28days	14days	28days	14days	28days
1	0ml	5.68	6.24	5.68	6.24	5.68	6.24
2	5ml	5.72	6.46	5.92	6.72	5.88	6.68
3	10ml	5.86	6.74	6.1	6.92	6.04	6.88
4	15ml	5.76	6.52	5.96	6.8	5.9	6.7
5	20ml	5.62	6.4	5.84	6.64	5.8	6.5

For M40 Grade Concrete

S.no	Bacteria used	Split tensile strength of concrete by using Bacillus pasteurii		Split tensile strength of concrete by using Bacillus subtilis		Split strength of concrete by using Bacillus sphaericus	
		14days	28days	14days	28days	14days	28days
		14days	28days	14days	28days	14days	28days
1	0ml	5.94	6.24	5.94	6.24	5.94	6.24
2	5ml	6.12	6.44	6.16	6.28	6.2	6.3
3	10ml	6.26	6.78	6.26	6.34	6.32	6.38
4	15ml	6.14	6.62	6.1	6.22	6.18	6.26
5	20ml	6.08	6.54	5.94	6.08	6.04	6.12

Flexural strength of concrete

For M30 Grade Concrete

S.no	Bacteria used	Flexural strength of concrete by using Bacillus pasteurii		Flexural strength of concrete by using Bacillus subtilis		Flexural strength of concrete by using Bacillus sphaericus	
		14days	28days	14days	28days	14days	28days
		14days	28days	14days	28days	14days	28days
1	0ml	4.46	5.12	4.46	5.12	4.46	5.12
2	5ml	4.62	5.2	4.96	5.22	4.88	5.2
3	10ml	4.84	5.36	5.26	5.34	5.28	5.4
4	15ml	4.74	5.22	5.16	5.24	5.1	5.26
5	20ml	4.6	5.04	5.04	5.12	5.08	5.16

For M40 Grade Concrete

S.no	Bacteria used	Flexural strength of concrete by using Bacillus pasteurii		Flexural strength of concrete by using Bacillus subtilis		Flexural strength of concrete by using Bacillus sphaericus	
		14days	28days	14days	28days	14days	28days
		14days	28days	14days	28days	14days	28days
1	0ml	4.68	5.24	4.68	5.24	4.68	5.24
2	5ml	4.84	5.34	4.96	5.62	4.94	5.58
3	10ml	4.98	5.48	5.06	5.84	5.08	5.94
4	15ml	4.88	5.26	4.96	5.72	5.04	5.68
5	20ml	4.62	5.12	4.72	5.56	4.68	5.48

Durability**Acid attack****% Loss of weight**

% Bacteria used	M30 Grade Concrete			M40 Grade Concrete		
	Bacillus Pasteurii	Bacillus Subtilis	Bacillus sparsicus	Bacillus Pasteurii	Bacillus Subtilis	Bacillus sparsicus
0ml	0.82	1.24	1.24	1.16	1.24	1.38
5ml	0.94	1.36	1.38	1.32	1.38	1.54
10ml	1.2	1.58	1.58	1.48	1.52	1.74
15ml	1.44	1.82	1.72	1.86	1.88	1.98
20ml	1.6	1.98	1.98	2.04	1.98	2.1

% Loss of compressive strength

% Bacteria used	M30 Grade Concrete			M40 Grade Concrete		
	Bacillus Pasteurii	Bacillus Subtilis	Bacillus sparsicus	Bacillus Pasteurii	Bacillus Subtilis	Bacillus sparsicus
0ml	6.64	7.12	7.12	6.72	7.24	7.12
5ml	7.4	7.32	7.68	6.98	7.38	7.34
10ml	7.8	7.64	8.24	7.14	7.58	7.62
15ml	8.4	8.14	8.8	7.34	7.84	7.98
20ml	9.2	8.54	9.3	7.84	8.12	8.16

Alkaline attack**% Loss of weight**

% Bacteria used	M30 Grade Concrete			M40 Grade Concrete		
	Bacillus Pasteurii	Bacillus Subtilis	Bacillus sparsicus	Bacillus Pasteurii	Bacillus Subtilis	Bacillus sparsicus
0ml	1.2	1.32	1.46	1.34	1.36	1.56
5ml	1.44	1.48	1.58	1.46	1.48	1.76
10ml	1.6	1.64	1.72	1.58	1.66	1.88
15ml	1.84	1.88	1.88	1.78	1.84	1.98
20ml	1.96	2.04	2.14	1.96	2.1	2.18

% Loss of compressive strength

% Bacteria used	M30 Grade Concrete			M40 Grade Concrete		
	Bacillus Pasteurii	Bacillus Subtilis	Bacillus sparsicus	Bacillus Pasteurii	Bacillus Subtilis	Bacillus sparsicus
0ml	8.23	8.14	9.64	8.54	9.28	9.14
5ml	8.68	9.38	9.72	8.98	9.46	9.38
10ml	8.42	9.64	9.98	9.34	9.82	9.64
15ml	9.1	9.84	10.18	9.68	10.14	9.84
20ml	9.62	9.96	10.38	9.98	10.26	9.96

Sulphate attack**% Loss of compressive strength**

% Bacteria used	M30 Grade Concrete			M40 Grade Concrete		
	Bacillus Pasteurii	Bacillus Subtilis	Bacillus sparsicus	Bacillus Pasteurii	Bacillus Subtilis	Bacillus sparsicus
0ml	12.66	13.24	13.82	12.66	14.12	13.68
5ml	12.88	13.66	13.74	12.98	14.36	13.98
10ml	13.4	14.12	13.98	13.4	14.84	14.32
15ml	12.6	14.54	14.18	12.8	15.04	14.88
20ml	13.8	14.88	14.48	13.8	15.22	15.18

Healing of concrete

The crack made in the Concrete Cube made up of **Bacillus Subtilis**

The crack on the concrete Cube made up of **Bacillus Subtilis** after allowed for Self healing



The crack made in the Concrete Cube made up of **Bacillus Subtilis**

The crack on the Concrete Cube made up of **Bacillus subtilis** after allowed for Self-healing




The crack made in the Concrete Cube made up of **Bacillus Pasteurii**

The crack on the Concrete Cube made up of **Bacillus Pasteurii** after allowed for



The fig shows the crack made in the Concrete Cube made up of **Bacillus Pasteurii**

The crack on the Concrete Cube made up of **Bacillus Pasteurii** after allowed for Self healing



The crack made in the Concrete Cube made up of **Bacillus Sphaericus**

The crack on the Concrete Cube made up of **Bacillus Sphaericus** after



The crack made in the Concrete Cube made up of **Bacillus Sphaericus**

The crack on the Concrete Cube made up of **Bacillus Sphaericus** after allowed for Self healing

1. The value slump increases with increasing the bacteria content in concrete. Whereas the value of compaction factor decreases with increasing the bacteria content in concrete.
2. Initially the values of compressive strength, split tensile strength and flexural strength of bacterial concrete increases up to 10ml bacteria content after that the value of compressive strength decreases with increase in the bacteria content in concrete the optimum value of strength of bacterial concrete was observed at 10ml bacteria.
3. In case of durability by using acid attack and alkalinity attack and sulphate attack the values of percentage lose of weight and percentage lose of strength increases with increase in the bacteria content in all the cases.
4. Bacterial concrete also drastically inspired the durability characteristics of the shape via healing of cracks within the structure. Due to its inherent capacity to precipitate calcite continuously bacterial concrete is also called as a 'Smart Bio fabric'.
5. Due to its green and self-recovery capability it's been proved to be better than the traditional concrete. Bacterial concrete will soon be evolved in constructing of long lasting, fee powerful and surroundings friendly.

So the optimal value of strength was observed at 10ml of Bacteria for M30 Grade concrete and M40 Grade concrete.

VI CONCLUSIONS

From the above experimental study the following conclusions were made

REFERENCES

1. Dr. S. Siddiraju, N. Ganesh Babu, "Behaviour of Bacterial Concrete", International Journal of Science and Research (IJSR), Volume 5 Issue 8, August 2016.

2. Sakina Najmuddin Saifee, Divya Maheshbhai Lad, Jayesh Rameshbhai Juremalani. Critical appraisal on Bacterial Concrete, IJRDO-Journal Of Mechanical And Civil Engineering, ISSN: 2456-1479, Volume-1, Issue-3, March 2015, PP 10-14 [2] Meera C.M, Dr.Subha V. Strength and Durability assessment Of Bacteria Based Self-Healing Concrete. IOSR Journal of Mechanical and Civil Engineering, e-ISSN: 2278-1684 , PP 01-07
3. Ravindranatha, N. Kannan, Likhith M. L .Self healing material bacterial concrete, International Journal of Research in Engineering and Technology, Volume: 03,Special Issue: 03, May-2014,NCRIET-2014, PP 656-659
4. A.T.Manikandan, A.Padmavathi. An Experimental Investigation on Improvement of Concrete Serviceability by using Bacterial Mineral Precipitation Volume II, Issue III, March 2015 IJRSI
5. Jagadeesha Kumar B G, R Prabhakara, Pushpa H. Effect Of Bacterial Calcite Precipitation On Compressive Strength Of Mortar Cube, International Journal of Engineering and Advanced Technology (IJEAT), ISSN: 2249 – 8958, Volume-2, Issue-3, February 2013,PP 486-491.
6. RA. B. Depaa and T. Felix Kala Experimental Investigation of Self Healing Behavior of Concrete using Silica Fume and GGBFS as Mineral Admixtures Indian Journal of Science and Technology, Vol 8(36), DOI: 0.17485/ijst/2015/v8i36/87644, December 2015.
7. Chithra P, BaiShibi Varghese. An experimental investigation on the strength properties of fly ash based bacterial concrete International Journal of Innovative Research in Advanced Engineering (IJIRAE) ISSN: 2349-2763 Issue 08, Volume 3 (August 2016)
8. V Srinivasa Reddy, M V SeshagiriRao, S Sushma. Feasibility Study on Bacterial Concrete as an innovative self crack healing system. International Journal of Modern Trends in Engineering and Research, e-ISSN No.:2349-9745, Volume 2, Issue 7, [July-2015] Special Issue of ICRTET'2015, Date: 2-4 July, 2015, PP 642-647.
9. Ashish Babarao Gawande, Yash Suneel Khandekar and Ojas Pravin Rahate, Applicability of Concrete Treated with Self-Healing Bacterial Agents. International Journal of Civil Engineering and Technology, 7(5), 2016, pp.275–283.
10. Abhishek Thakur, Akshay Phogat and Khushpreet Singh, Bacterial Concrete and Effect of Different Bacteria on the Strength and Water Absorption Characteristics of Concrete: A Review. International Journal of Civil Engineering and Technology, 7(5), 2016, pp.43–56.
11. MohitGoyal, P. Krishna Chaitanya. Behaviour of Bacterial Concrete as Self Healing Material, International Journal of Emerging Technology and Advanced Engineering ,ISSN 2250-2459, Volume 5, Issue 1, January 2015,PP 100-103
12. N.GaneshBabu. An experimental study on strength and fracture properties of self healing concrete ,International Journal of Civil Engineering and Technology (IJCIET),Volume 7, Issue 3, May–June 2016, PP. 398–406.